



Overview

Canrez® CP75BK40 is a versatile FFKM material offering near universal chemical resistance and excellent high-temperature resistance at a low cost. Compare it to Kalrez 6375, 4079, and 7075.

CP75BK40 has a service temperature range of -20°C to 320°C and withstands short excursions outside that range.

Features & Benefits

- Near universal chemical resistance
- High Temperature Resistance
- Low Compression Set
- Cost Effective

Recommended Applications

- Semiconductor
- Chemical Processing
- Solvents, MEK, DMF, Acetone
- Esters, Ethers, Ketones, Aldehydes, Xylene
- Sour Gas < 65%

Service Temperature

- -20°C to 320°C (-4°F to 610°F)
- Steam < 300°C (580°F)
- Amines < 38°C (100°F)



Test Data

Table 1. Physical Properties

Color	Black
Hardness, Shore A	75
Tensile Strength, psi (MPa)	2132 (14.7)
Elongation	170%
100% Modulus, psi (MPa)	1624 (11.2)
Specific Gravity, g/cm ³	2.00
Fluorine Percentage	72.5%
Linear Coefficient of Thermal Expansion (1/°C)	3.5 x 10 ⁻⁴

Table 2. Compression Set

70hrs at 200°C	20%
70hrs at 280°C	34%
336hrs at 200°C	28%
336hrs at 230°C	41%

Table 3. Specific Heat

50°C, J/g	0.98
100°C, J/g	1.05
150°C, J/g	1.12

Table 4. Gas Permeation Rate (T=30°C)

Oxygen (cm ³ (STP)·mm/m ² ·atm·d)	440
Nitrogen (cm ³ (STP)·mm/m ² ·atm·d)	258
Helium (cm ³ (STP)·mm/m ² ·atm·d)	5400



High Temperature Aging

Table 5. Heat Aging – 70 hrs at 300°C

Hardness, Shore A	+1
Tensile Strength Change, %	-16
Ultimate Elongation Change, %	+10
Weight Change, %	+0

Table 6. Steam – 168 hrs at 300°C

Hardness, Shore A	+0
Tensile Strength Change, %	+14
Ultimate Elongation Change, %	-17
Weight Change, %	-1

Table 7. Water – 168 hrs at 225°C

Hardness, Shore A	-2
Tensile Strength Change, %	-14
Ultimate Elongation Change, %	+22
Volume Change, %	+2

Looking for specific chemical compatibilities or desire more material information? [Please Contact Us!](#)

Chemical Compatibility

Table 8. Toluene – 168 hrs at 150°C

Hardness, Shore A	-3
Tensile Strength Change, %	+4
Ultimate Elongation Change, %	+4
Weight Change, %	+8

Table 9. MEK – 720 hrs at 45°C

Hardness, Shore A	-3
Tensile Strength Change, %	+0
Ultimate Elongation Change, %	+0
Weight Change, %	+7

Table 10. HCL, 37% – 72 hrs at 80°C

Hardness, Shore A	+0
Tensile Strength Change, %	-2
Ultimate Elongation Change, %	-10
Volume Change, %	+3

Table 11. Glacial Acetic Acid – 336 hrs at 100°C

Hardness, Shore A	-12
Tensile Strength Change, %	-30
Ultimate Elongation Change, %	-1
Volume Change, %	+3

Table 12. MDEA – 168 hrs at 100°C

Hardness, Shore A	-3
Tensile Strength Change, %	+0
Ultimate Elongation Change, %	+3
Volume Change, %	+2

Table 13. Nitric Acid, 65% – 168 hrs at 80°C

Hardness, Shore A	-10
Tensile Strength Change, %	-25
Ultimate Elongation Change, %	+7
Volume Change, %	+8