



O-Ring Division
2360 Palumbo Drive
Lexington, KY 40509
(859) 269-2351

Date: 6/30/2006
Compound: E0603-70
Batch: 60007401
Test Specimen: T0606075
Test Lab Location: LEXINGTON
Page: 1 OF 1

COMPOUND DATA SHEET

<u>Original Physical Properties</u>	<u>Test Method</u>	<u>Test Results</u>
Hardness, Shore A, pts.	ASTM D2240	70
Tensile Strength, psi	ASTM D412	2140
Ultimate Elongation, %	ASTM D412	257
Specific Gravity	ASTM D297	1.20
 <u>Compression Set</u>		
70 hrs. @ 248°F(120°C)		
Percent of Original Deflection, max	ASTM D395 Method B	13
 <u>Dry Heat Resistance</u>		
70 hrs. @ 248°F(120°C)		
Hardness Change, pts.	ASTM D573	+6
Tensile Change, %		+2
Elongation Change, %		+4
 <u>Fluid Immersion</u>		
<u>Ethylene Glycol, 70 hrs. @ 212°F(100°C)</u>		
Hardness Change, Shore A pts.	ASTM D471	+4
Tensile Strength Change, %		0
Ultimate Elongation Change, %		-4
Volume Change, %		-2
 <u>Low Temperature TR-10</u>		
	ASTM D1329	-49°C
 <u>Low Temperature Brittleness</u>		
Nonbrittle after 3 min. @ -25°C	ASTM D2137	pass

"Purchaser use only. Reproduce only in full. Data pertains to items referenced only."
"The recording of false, fictitious, or fraudulent statements or entries on this report may be punishable as a felony under federal law."