



Chemraz® 584 Sealing Solutions

Compound No./Material Name:	Rubber Classification:	Service Temperature Range:	Color:
Chemraz® 584	FFKM	-30°C to 220°C (-22°F to 428°F)	Cream

Description	Typical
Original Properties (ASTM Standard)	
Specific Gravity (D297)	1.98
Hardness, Shore A, Points (D2240)	70
Tensile Strength, psi (D1414)	1300
Elongation, % (D1414)	145
Modulus @ 50% Elongation, psi (D1414)	350
Modulus @ 100% Elongation, psi (D1414)	780
Compression Set @ 25% Deflection (ASTM Standard)	
70 Hours @ 400°F, in Air, % of Original Deflection (D395)	35

Note: Unless otherwise noted, all tests performed on 214 o-rings.

Contact Us

Greene Tweed
Houston, TX, USA

Tel: +1.281.765.4500
Fax: +1.281.821.2696

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.

© 2018, Greene Tweed all rights reserved. All trademarks are property of their respective owners.

08/18-GT DS-US-GE-051