



Overview

HN75BK00 is Canyon's standard 70 shore A durometer, black HNBR. Hydrogenated NBR offers improved thermal performance over standard NBR materials. Compare to Parker N1173-70, KA174-75, and KA157-70.

Features & Benefits

- Good abrasion resistance
- Improved high temperature performance & chemical resistance
- Low Compression Set
- Cost Effective

Service Temperature

- -35°C to 163°C (-30°F to 325F)

Specification

- ASTM D2000 M3DH710 A26 B36 E016 E036 F19 Z1

Test Data

Table 1. Physical Properties		
Test	Requirements	Results
Color	Black	Black
Hardness, Shore A	75+/-5	75
Tensile Strength, psi (MPa)	1450 min	3467 (23.9)
Elongation	200% min	305%
Specific Gravity, g/cm ³		1.26



Table 2. A26 - Heat Aging - 70 hrs at 150°C

Test (Change)	Requirements	Results
Hardness, Shore A	+10 max	+1
Tensile Strength, %	-25 max	-2
Elongation, %	-30 max	-1

Table 3. B36 - Compression Set - 22 hrs at 150°C

Test (Change)	Requirements	Results
Permanent Set, %	50 max	22

Table 4. E016 - ASTM Oil #1 (901) Resistance - 70 hrs at 150°C

Test (Change)	Requirements	Results
Hardness, Shore A	-5 to +10	+1
Tensile Strength, %	-20 max	+1
Elongation, %	-30 max	-4
Volume, %	-5 to +5	-1.5

Table 5. E036 - ASTM Oil #3 (903) Resistance - 70 hrs at 150°C

Test (Change)	Requirements	Results
Hardness, Shore A	-15 max	-5
Tensile Strength, %	-30 max	-3
Elongation, %	-30 max	-10
Volume, %	+25 max	+10

Table 6. F17 - Low Temp Brittleness Test - 3 mins at -55°C

Test (Change)	Requirements	Results
Brittleness	Non-Brittle	Non-Brittle