



# COMPOUND DATA SHEET

Parker O-Ring Division, North America

## MATERIAL REPORT

LTR Report Number: 95610  
Date: 7/11/2013

**Title:** Evaluation of Parker Compound S0455-70

**Elastomer Type:** Silicone (VMQ, PVMQ)

**Purpose:** To obtain typical test data.

**Specification:** ASTM D2000 M7GE705 A19 B37 EA14 E016 E036 F19 G11 Z1 (Specific Gravity)  
Z2 (Elongation %, minimum 110)

**Color:** Rust

**Recommended Temperature Range:** -65°F to 450°F/500°F

**Recommended For:** Animal, Vegetable oil, and grease, high molecular weight chlorinated aromatic hydrocarbons (including flame-resistant insulators, and coolant for transformers), moderate water resistance, diluted salt solutions, ozone, aging, and weather resistance.

**Not Recommended For:** Superheated water/steam over 250°F, acids and alkalis, low molecular weight chlorinated hydrocarbons (trichloroethylene), hydrocarbon based fuels, aromatic hydrocarbons (benzene, toluene), low molecular weight silicone oils.

**Additional Approvals:** N/A

## REPORT DATA

<u>Original Physical Properties</u>	<u>Test Method</u>	<u>Spec Limits</u>	<u>Test Results</u>
Hardness, Shore A, pts.	ASTM D2240	70 ±5	68
Tensile Strength, PSI	ASTM D412	725	888
<b>(Z2)</b> Ultimate Elongation, %	ASTM D412	110	118
<b>(Z1)</b> Specific Gravity	ASTM D297	report	1.28
<b>(B37) Compression Set (Plied)</b>			
<b><u>22 hrs. @ 347°F</u></b>			
Percent of Original Deflection, Max	ASTM D395 Method B	30	11
<b>(A19) Heat Age</b>			
<b><u>70 hrs. @ 437°F</u></b>			
Hardness Change, pts.	ASTM D573	+10	+4
Tensile Strength Change, %		-25	+3
Ultimate Elongation Change, %		-30	-3
<b>(EA14) Fluid Resistance</b>			
<b><u>Water, 70 hrs @ 212°F</u></b>			
Hardness Change, pts.	ASTM D471	± 5	-3
Volume Change, %		± 5	+1
<b>(E016) Fluid Resistance</b>			
<b><u>IRM 901, 70 hrs @ 302°F</u></b>			
Hardness Change, pts.	ASTM D471	-0 to -15	-5
Tensile Strength Change, %		-20	-5
Ultimate Elongation Change, %		-20	+5
Volume Change, %		0 to +15	+6
<b>(E036) Fluid Resistance</b>			
<b><u>IRM 903, 70 hrs @ 302°F</u></b>			
Hardness Change, pts.	ASTM D471	-40	-18
Volume Change, %		+60	+41
<b>(G11) Tear Resistance</b>			
<u>kN/m, min.</u>	ASTM D624	9	12
<b><u>(F19) Low Temperature Resistance</u></b>			
Nonbrillite after 3 min @ -67°F	ASTM D1329	pass/fail	Pass

"Purchaser use only. Reproduce only in full. Data pertains to items referenced only."

"The recording of false, fictitious, or fraudulent statements or entries in this report may be punishable as a felony under federal law."

Parker O-Ring Division  
2360 Palumbo Drive  
Lexington, Ky 40509  
(859) 269-2351