



Overview

VT75BU02 is Canyon's FDA Compliant, 75 shore A durometer, blue FKM Type A. This is an extremely popular, cost-effective material. Other FKM types are also available: A, B, F, GF, GLT, GFLT, ULT, ETP.

Features & Benefits

- FDA Compliant CFR 21 177.2600
- Great heat resistance & high temp stability
- Excellent chemical resistance
- Excellent resistance to weathering and aging

Service Temperature

- -26°C to 225°C (-15°F to 437F)

Specification

- ASTM D2000 M6HK810 A1-10 B38 C12 C20 EF31 E088

Test Data

Table 1. Physical Properties		
Test	Requirements	Results
Color	Blue	Blue
Hardness, Shore A	75+/-5	76
Tensile Strength, psi (MPa)	1450 min	1770 (12.2)
Elongation	150% min	160%



Table 2. A1-10 - Heat Aging - 70 hrs at 250°C

Test (Change)	Requirements	Results
Hardness, Shore A	+10 max	+2
Tensile Strength, %	-25 max	+4
Elongation, %	-25 max	-8

Table 3. B38 - Compression Set - 22 hrs at 200°C

Test (Change)	Requirements	Results
Permanent Set, %	15 max	13.9

Table 4. EF31 - Fuel C Resistance - 70 hrs at 23°C

Test (Change)	Requirements	Results
Hardness, Shore A	-5 to +5	-1
Tensile Strength, %	-25 max	-14
Elongation, %	-20 max	-12
Volume, %	-0 to +10	+3

Table 5. E088 - SAE Fluid #2 / Stauffer 7700 Resistance - 70 hrs at 200°C

Test (Change)	Requirements	Results
Hardness, Shore A	-15 to +5	-6
Tensile Strength, %	-40 max	-21
Elongation, %	-20 max	-14
Volume, %	+25	+8

VT75BU02 is now available on the Canyon Components [online store!](#)