



Overview

VT75WH00 is Canyon's standard 75 shore A durometer, white FKM Type A. This is an extremely popular, cost-effective commodity material. Other FKM types are also available: A, B, F, GF, GLT, GFLT, ULT, ETP. Compare to Parker V1164-75, V1476-75, and V1475-75.

Features & Benefits

- Great heat resistance & high temp stability
- Excellent chemical resistance
- Excellent resistance to weathering and aging

Service Temperature

- -26°C to 225°C (-15°F to 437°F)

Specification

- ASTM D2000 M6HK810 A1-10 B38 EF31 E088

Test Data

Table 1. Physical Properties		
Test	Requirements	Results
Color	White	White
Hardness, Shore A	75+/-5	76
Tensile Strength, psi (MPa)	1450 min	2200 (15.2)
Elongation	150% min	180%



Table 2. A1-10 - Heat Aging - 70 hrs at 250°C

Test (Change)	Requirements	Results
Hardness, Shore A	+10 max	+2
Tensile Strength, %	-25 max	+3
Elongation, %	-25 max	-6

Table 3. B38 - Compression Set - 22 hrs at 200°C

Test (Change)	Requirements	Results
Permanent Set, %	15 max	9

Table 4. EF31 - Fuel C Resistance - 70 hrs at 23°C

Test (Change)	Requirements	Results
Hardness, Shore A	-5 to +5	-1
Tensile Strength, %	-25 max	-10
Elongation, %	-20 max	+3
Volume, %	-0 to +10	+1

Table 5. E088 - Blend 7700 Resistance - 70 hrs at 200°C

Test (Change)	Requirements	Results
Hardness, Shore A	-15 to +5	-7
Tensile Strength, %	-40 max	-19
Elongation, %	-20 max	+4
Volume, %	+25 max	+8

VT75WH00 is now available on the Canyon Components [online store!](#)